











Pigment















[®]
RIVOCEM
INDUSTRIES PVT LTD

MICROFAST[®]

Phthalocyanine Pigments

Phthalocyanine Pigments	MICROFAST Green 7 RV	MICROFAST Alpha Blue RV 6010	MICROFAST Alpha Blue RV 6021	MICROFAST Beta Blue RV 6040
Color Index No.	74260	74160	74160	74160
Specific Gravity	1.6	1.4	1.39	1.4
Bulk Density (L/kg)	5	4	4.2	4.1
Oil Absorption (gms/100gms)	35	45	45	42
Ph of Aqueous Extract	7	7	7	7
Full Shade	8	7	8	8
Tint Shade	8	6	8	8
Heat Resistance	280	200	280	280
Mass Tone				
Tint Tone				

Inorganics Pigments

Inorganics Pigments	Microfast Middle Chrome (C. I. Pigment Yellow 34)	Microfast Lemon Chrome (C. I. Pigment Yellow 34)	Microfast Prime Rose Chrome (C. I. Pigment Yellow 34)	Microfast Scarlet Chrome (C. I. Pigment Red 104)	Microfast Ultramarine Blue (C. I. Pigment Blue 29)	Microfast Green (C. I. Pigment Green 8)
Color Index No.	77603	77603	77603	77605	77007	10006
Specific Gravity	5.5	5.2	5.1	5.9	2.3	1.45
Bulk Density (L/kg)	4.5	4.5	5	4.5	4.1	5
Oil Absorption (gms/100gms)	29	26	30	22	23	39
Ph of Aqueous Extract	1.39	6-7	7	6-7	7	7
Full Shade	7-8	7-8	6	7	8	7
Tint Shade	7-8	7-8	5-6	7	8	6-7
Heat Resistance	250	250	250	250	250	200
Mass Tone						
Tint Tone						

This is for representation, original might differ.